

SEALS AND COUPLING MATERIALS USING TABLE

NBR (Nitrile)	FPM (Viton)	EPDM	PTFE (Teflon)
<p>Main properties: Resistant to oil and petrol good ageing characteristics, high abrasion resistance.</p> <p>Als Dichtungswerkstoffe stehen folgende Serienqualitäten zur Verfügung: Perbunan, Hauptigenschaften: Beständigkeit gegen Öl und Benzin gute Alterungsbeständigkeit, hoher Schutz gegen Abrieb.</p>	<p>Main properties: Outstanding heat resistant performance, excellent resistance to oils, chemicals, solvent, active oxygen, and weather.</p> <p>Viton, Hauptigenschaften: Überragende Hitzebeständigkeit, ausgezeichnete Beständigkeit gegen Ole, Chemikalien, Lösungsmittel, Ozon, Sauerstoff und Witterung.</p>	<p>Main properties Ethylen Propylene, High mechanical strength, excellent resistance to high and low temperatures and to active oxygen and weather. Good resistance to chemical media.</p> <p>EP-Athylen Propylen, Hauptigenschaften: Hohe mechanische Festigkeit. Ausgezeichnete Wärme- und Kältebeständigkeit. Hervorragende Beständigkeit gegen Ozon- und Witterungseinflüsse. Gute chemische Beständigkeit.</p>	<p>For very aggressive media special constructions with PTFE seals (Teflon) are available. Für sehr aggressive Medien sind Sonderkonstruktionen mit PTFE-Dichtungen (Teflon) verfügbar: Alle Angaben sind unverbindlich und dienen nur zur Orientierung. Sie gelten 1. für reine Stoffe, 2. wenn nicht anders angegeben für Raumtemperatur. 3. bei Säuren, Säuren usw., für wäßrige Lösungen mäßiger Konzentrationen. Teflon-eingetragenes 'Dupont'-Warenzeichen.</p>

Symbols - Korrosionstabelle	Material	Seal Dichtung																				
<ul style="list-style-type: none"> ✓ Fully resistant / beständig D Partly resistant / bedingt — Non-resistant / nicht 	<table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th>Steel zinc plated</th> <th>Stahl Verzinkt</th> <th>Brass - Messing</th> <th>AISI 316 Ti or similar</th> <th>Edelstahl AISI 316 Ti</th> <th>Polyamide 11/12</th> <th>Polyacetal - Poliasetal</th> <th>NBR Nitrile</th> <th>FPM Viton</th> <th>EPDM</th> </tr> </thead> <tbody> <tr> <td>✓</td><td>✓</td><td>✓</td><td>✓</td><td>✓</td><td>✓</td><td></td><td></td><td></td><td>X</td></tr> </tbody> </table>	Steel zinc plated	Stahl Verzinkt	Brass - Messing	AISI 316 Ti or similar	Edelstahl AISI 316 Ti	Polyamide 11/12	Polyacetal - Poliasetal	NBR Nitrile	FPM Viton	EPDM	✓	✓	✓	✓	✓	✓				X	
Steel zinc plated	Stahl Verzinkt	Brass - Messing	AISI 316 Ti or similar	Edelstahl AISI 316 Ti	Polyamide 11/12	Polyacetal - Poliasetal	NBR Nitrile	FPM Viton	EPDM													
✓	✓	✓	✓	✓	✓				X													
Acetate (Ethyl Acetate & Amyl Acetate)	✓ ✓ ✓ ✓ ✓	X																				
Acetic acid 10%	— ✓ — — ✓	X																				
Acetone	✓ ✓ ✓ ✓ ✓	X																				
Acetylene	✓ ✓ ✓ ✓ ✓	X X X																				
Aero Engine Fuel BP, Esso Avgas 100/130	✓ ✓ ✓ ✓ D	X X																				
Aero Engine Oil BP : AIRO 1210, Esso: AVIATON-120 Shell: AIRO-120, DERD 2487 DERD 2497, DTD 585	✓ ✓ ✓ ✓ D	X X																				
Skydrol	✓ — ✓ — —	X																				
Oronite	✓ — ✓ — —	X																				
Air, compressed	✓ ✓ ✓ ✓ ✓	X X																				
Air, hot up to 120°C	✓ ✓ ✓ D	X X																				
Air, hot up to 200°C	✓ ✓ ✓ — —	X																				
Alcohol	✓ ✓ ✓ ✓ ✓	X																				
Alum	— ✓ ✓ ✓ ✓	X X X																				
Alkalies	— D ✓ ✓ D	X X																				
Ammonia, Liquid	D — ✓ ✓ —	X																				
Ammonium Sulphate Solution	— — ✓ ✓ D	X X X																				
Amyl Alcohol	✓ ✓ ✓ ✓ ✓	X																				
Aniline	✓ — ✓ D	X																				
Benzole	✓ ✓ ✓ ✓ ✓	X																				
Borax	✓ ✓ ✓	X X																				
Bultane	✓ ✓ ✓ ✓ ✓	X X																				
Bultane	✓ ✓ ✓	X X																				
Butyl Alcohol	— ✓ ✓ ✓ ✓	X																				
Carbon Dioxide	— ✓ ✓ ✓ ✓	X X X																				
Carbon Dioxide, dry	✓ ✓ ✓ ✓	X X X																				
Carbon Dioxide liquid	— ✓ ✓ ✓ D	X X X																				
Carbon Bisulphide	✓ ✓ ✓	X																				
Chloride of Barium	✓ D ✓ ✓	X X X																				
Chromic Acid	— — D D —	X																				
Citric Acid	— D ✓ — D	X X																				
Creosote	✓ ✓ ✓	X																				
Cresol	D ✓ ✓ — —	X																				
Cresol, Cresylic Acid	✓ ✓	X																				
Cupric Chloride	✓ D —	X X X																				
Cyclohexane	✓ ✓ D ✓	X																				
Dimethylamine	✓ ✓	X																				
Emulsion. (Water/Oil)	D ✓ ✓ ✓ ✓	X X																				
Ether	✓ ✓ ✓ ✓ ✓	X																				

Symbols - Korrosionstabelle	Material	Seal Dichtung																				
<ul style="list-style-type: none"> ✓ Fully resistant / beständig D Partly resistant / bedingt — Non-resistant / nicht 	<table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th>Steel zinc plated</th> <th>Stahl Verzinkt</th> <th>Brass - Messing</th> <th>AISI 316 Ti or similar</th> <th>Edelstahl AISI 316 Ti</th> <th>Polyamide 11/12</th> <th>Polyacetal - Poliasetal</th> <th>NBR Nitrile</th> <th>FPM Viton</th> <th>EPDM</th> </tr> </thead> <tbody> <tr> <td>✓</td><td>✓</td><td>✓</td><td>✓</td><td>✓</td><td>✓</td><td>✓</td><td>✓</td><td>✓</td><td>X X</td></tr> </tbody> </table>	Steel zinc plated	Stahl Verzinkt	Brass - Messing	AISI 316 Ti or similar	Edelstahl AISI 316 Ti	Polyamide 11/12	Polyacetal - Poliasetal	NBR Nitrile	FPM Viton	EPDM	✓	✓	✓	✓	✓	✓	✓	✓	✓	X X	
Steel zinc plated	Stahl Verzinkt	Brass - Messing	AISI 316 Ti or similar	Edelstahl AISI 316 Ti	Polyamide 11/12	Polyacetal - Poliasetal	NBR Nitrile	FPM Viton	EPDM													
✓	✓	✓	✓	✓	✓	✓	✓	✓	X X													
Ethyl Alcohol	✓	X X																				
Ethylene	✓ ✓	X																				
Formalin	✓ ✓	X X X																				
Formic Acid	— D	— — X																				
Frigen	✓ ✓	X X																				
Gasoline, Refined	✓	X X																				
Gas, Blast Furnace	D ✓ ✓	X																				
Gas, Coal	D ✓ ✓	X																				
Gas, Coke Oven	D ✓ ✓	X																				
Gas, Lighting	✓ ✓ ✓	X X																				
Gas, Naphtalene content	✓ ✓ ✓	X X																				
Gas, Natural	✓ ✓ ✓	X X																				
Gas, Town	✓ ✓ ✓	X																				
Gear Oil	✓	X X																				
Glucose	✓ ✓ ✓	X X X																				
Glycerine	✓ ✓ ✓	X X X																				
Glycol	✓ ✓ ✓	X X																				
Helium	✓ ✓ ✓	X X X																				
Hexane	✓	X X																				
Hydrocarbons	✓ ✓ ✓	X X																				
Hydrogen	✓ ✓ ✓	X X																				
Hydrogen Gas	✓	X X																				
Hydrogen Sulphide, Humid	D ✓ ✓	X																				
Hydrogen Sulphide, dry	✓ ✓	X																				
Hydrogen Peroxide 30%	— — ✓ ✓	X																				
Isopropyl Alcohol	✓ ✓ D ✓	X X X																				
Kerosene, JP 1	✓ ✓ ✓ ✓ ✓	X X																				
Keton, Methyl Ethyl	✓ ✓ ✓ ✓ ✓	X																				
Latex, liquid up to 130°C	✓ ✓ ✓ D D	X																				
Lubricating Oil	✓ ✓ ✓ ✓ ✓	X X																				
Lye, Caustic	— ✓ ✓ ✓ D	X																				
Lye, Hyochorous Acid	— ✓ — D	X																				
Lye, Pickling	— MS60 ✓ D D	X																				
Magnesium Carbonate	✓ ✓ ✓ ✓ ✓	X X X																				
Magnesium Hydroxide	✓ ✓ ✓ ✓ ✓	X X X																				
Magnesium Sulphate. M.Sulfat	— ✓ ✓ ✓ ✓	X X X																				
Mercury	✓ — ✓ ✓ ✓	X X X																				
Methane	✓ ✓ ✓ ✓ ✓	X X																				
Methanol	✓ ✓ ✓ ✓ ✓	X X																				
Methyl Alcohol	✓ ✓ ✓ D ✓	X X																				
Methyl Ethyl Ketone	✓ ✓ ✓ ✓ ✓	X																				

 |

SEALS AND COUPLING MATERIALS USING TABLE

NBR (Nitrile)	FPM (Viton)	EPDM	PTFE (Teflon)
<p>Main properties: Resistant to oil and petrol good ageing characteristics, high abrasion resistance.</p> <p>Als Dichtungswerkstoffe stehen folgende Serienqualitäten zur Verfügung: Perbunan, Haupteigenschaften: Beständigkeit gegen Öl und Benzin, gute Alterungsbeständigkeit, hoher Schutz gegen Abrieb.</p>	<p>Main properties: Outstanding heat resistant performance, excellent resistance to oils, chemicals, solvent, active oxygen, and weather.</p> <p>Viton, Haupteigenschaften: Überragende Hitzebeständigkeit, ausgezeichnete Beständigkeit gegen Ole, Chemikalien, Lösungsmittel, Ozon, Sauerstoff und Witterung.</p>	<p>Main properties Ethylen Propylene, High mechanical strength, excellent resistance to high and low temperatures and to active oxygen and weather. Good resistance to chemical media.</p> <p>EP,Athylen Propylen, Haupteigenschaften: Hohe mechanische Festigkeit. Ausgezeichnete Wärme- und Kältebeständigkeit. Hervorragende Beständigkeit gegen Ozon und Witterungseinflüsse. Gute chemische Beständigkeit.</p>	<p>For very aggressive media special constructions with PTFE seals (Teflon) are available. Für sehr aggressive Medien sind Sonderkonstruktionen mit PTFE-Dichtungen (Teflon) verfügbar: Alle Angaben sind unverbindlich und dienen nur zur Orientierung. Sie gelten 1.für reine Stoffe, 2. wenn nicht anders angegeben für Flammtemperatur. 3.bei Saizen, Säuren usw., für wäßrige Lösungen mäßiger Konzentrationen. Teflon-eingetragenes 'Dupont'-Warenzeichen.</p>

Symbols - Korrosionstabelle	Material					Seal Dichtung
	Steel zinc plated Stahl Verzinkt	Brass - Messing	AlSi 316 Ti or similar Edelstahl AlSi 316 Ti	Polyamide 11/12 Polyamid 11/12	Polyacetal - Poliasetal	NBR Nitrile
						FPM Viton
✓ Fully resistant / beständig						EPDM
D Partly resistant / bedingt						
— Non-resistant / nicht						
Methyl Benzene	✓		✓			X
Milk	✓	—	✓	✓	✓	X
Napta	✓		✓		✓	X X
Naptalene	✓	✓	✓	✓	✓	X
Naptenic. Acid	✓		✓			X X
Nitrate of Ammonium	✓		✓			X X X
Nitric Acid. up to 35°C	—	✓	✓	—	—	X
Nitrogen	✓	✓	✓	✓	✓	X X X
Nitro-Solution (no synthetic resin thinners)	✓	✓	✓	—	✓	X
Oil, Coal Tr	✓		✓	✓	D	X
Oil, Crude	✓	✓	✓	✓	✓	X X
Oil, Diesel	✓	✓	✓	✓	✓	X
Oil, Diesel up to 120°C		✓	✓	D	—	X
Oil, Fuel up to 100°C	✓	✓	✓	D	—	X X
Oil, up to 200°C/ 300°C up to (special type)	✓	D	✓	—	—	FFKM
Oil, Fuel 5x5	✓	✓	✓	D	✓	X
Oil, Hydraulic Chlorinated	D	D	✓	—	D	X
Oil, Hydraulic up to 120°C	✓	✓	✓	D	D	X X
Oil, Linseed	✓	✓	✓	✓	✓	X X
Oil, Mineral	D	✓	✓	✓	✓	X X
Oil, Transformer	D	D	✓	✓	D	X
Oleic Acid	✓	—	✓	✓	✓	X X
Oxalic Acid	D	D	✓	✓	✓	X X
Oxygen. fat free	—	✓	✓	✓	D	X
Paraffin	✓	✓	✓	✓	✓	X
Paraffin, (Wax)	✓	✓	✓	✓	✓	X
Pentachlorphenole	✓					X
Petrol Ether		✓	✓	✓	✓	X
Petrol	✓	✓	✓	✓	✓	X
Phenol Solution	D	✓	✓	—	—	
Phosphoric Acid 10%			✓	—	—	X X
Potassium Cyanide	✓	—	✓	✓	D	X X
Potassium Dichromate	✓	—	✓	—	D	X X
Potassium Sulphate	✓		✓			X X X
Potassium Hydroxide	✓		✓	✓	D	X
Propane	✓	✓	✓	✓	✓	X X
Prussic Acid	✓	—	✓			X
Salt Solution	—	D	D	✓	D	X
Sea Water	—	D		✓	X	X X X

Symbols - Korrosionstabelle	Material					Seal Dichtung		
	Steel zinc plated Stahl Verzinkt	Brass - Messing	AlSi 316 Ti or similar Edelstahl AlSi 316 Ti	Polyamide 11/12 Polyamid 11/12	Polyacetal - Poliasetal	NBR Nitrile	FPM Viton	EPDM
✓ Fully resistant / beständig								
D Partly resistant / bedingt								
— Non-resistant / nicht								
Soap Solution	—	✓	✓	✓	✓	X	X	X
Soap Solution	—	D	✓	✓	D	X	X	X
Sodium Acetate			✓	✓	✓	X		X
Sodium Bicarbonate			D	✓	✓		X	X
Sodium Carbonate	✓		✓	✓	✓	X	X	X
Sodium Chloride	✓		✓	✓	✓	X	X	X
Sodium Cyanide	✓		✓	—	D			X
Sodium Sulphide	✓	D	✓				X	X
Steam, up to 150°C	D	D	✓	—	—			X
Steam, up to 250°C	D	D	✓	—	—	PTFE		
Sulphide of barium	✓	D	✓	✓		X	X	X
Sulphur Dixide, Gas			✓	✓				X
Sulphuret of Carbon			✓	✓	—	✓		X
Syntetic Resin Thinners (no nitrosolution)	✓	✓	✓	D	D			X
Tar	✓	✓	✓	✓	✓	X	X	
Tetracholride of Titanium	✓		✓					X
Toluol, dry	D	✓	✓	✓	✓			X
Trichlorethylene	✓	D	✓	✓	—			X
Turbine Fuel, BP: ATK 2494, ES- SO:MIL-F56/16, SHELL:ATF 650	✓	✓	✓	✓	D	X	X	
Turbine Oil, Esso:35	✓	✓	✓	✓	D	X	X	
Turb-oil 1 S (MILL 7808)	D	D	✓	✓	D	X	X	
Vacuum (Strengthened Valve Springs)	✓	✓	✓	✓	✓			
Vegetable Oil	✓		✓	✓	✓	X	X	X
Water, Distilled			✓	✓	✓		X	X
Water, Deionized			✓			X	X	
Water, Demineralised			✓					X
Water, up to 80°C	D	✓	✓	D	D	X	X	X
Water, over 80°C	D	✓	✓	D	—	X	X	X
Water, Cooling	D	D	✓	✓	D	X	X	X
Xylene	✓	✓	✓	✓	✓			X

WATER PNEUMATIC HYDRAULIC ELECTRICAL ACCESORIES



Temperature Range - Temperaturbereich

Nitrile (N)	-20°C + 110°C (-4°F + 230°F)
FPM (V)	-20°C + 180°C (-4°F + 356°F)
EPDM (Ethylene Propylene)	-40°C + 150°C (-40°F + 302°F)

Working Pressure - Betriebsdruck

25 Bar (360 PSI)

Connection/Disconnection Pressure -
15 Bar (220 PSI)

Material of steel version / Material für die Stahl Version

Socket Body -	Steel tenifer threaded
Kupplungsgrundkörper	Stahl teneferiert
Back Part -	Steel zinc-nickel plated
Hinterteil	Stahl Zink-Nickel beschichtet
Sleeve -	Steel zink-nickel plated and orange painted
Hülse	Stahl Zink-Nickel beschichtet und orange Lackiert
Springs - Federn	Stainless steel - Edelstahl
Seals - Dichtungen	Nitrile (N)
Plug - Nippel	Steel tenifer threaded Stahl teneferiert
451	The sleeve orange colour plastic Hülse ist aus Kunststoff, farbe orange

Material of stainless steel version

Material für die Edelstahlversion

Socket Body -	Stainless steel
Kupplungsgrundkörper	Edelstahl
Back Part - Hinterteil	Stainless steel - Edelstahl
Sleeve - Hülse	Stainless steel - Edelstahl
Springs - Federn	Stainless steel - Edelstahl
Seals - Dichtungen	FPM (V)
Plug - Nippel	Stainless steel - Edelstahl

Advantages

- The system perfectly fits to the ISO 4414, EN 983 safety requirements.
- Plug profile perfectly fits to the ISO 6150-C & AFNOR-C
- 2 stage disconnection safety feature
- Negligible Connecting Force
- Smart and Ergonomic features
- Ease of Handling
- Optimised Size

Flow size - Nennweiten

450.03 / SV 1-Stage	3mm (1/8")
450.06 / SV 2-Stage	5.5mm (1/4")
450.08 / SV 2-Stage	8mm (3/8")
450.11 / SV 2-Stage	11mm (1/2")
451.06 / SV 2-Stage	5.5mm (1/4")
451.08 / SV 2-Stage	8mm (3/8")
452.06 / SV Coded	5.5mm (1/4")

3mm (1/8")

5.5mm (1/4")

8mm (3/8")

11mm (1/2")

5.5mm (1/4")

8mm (3/8")

5.5mm (1/4")

5.5mm (1/4")

8mm (3/8")

5.5mm (1/4")



Compatible - Kompatibilität

170.08
171.08
173.08
450.08
461.08 / SC-E1

Temperature Range - Temperaturbereich

Nitrile (N)	-20°C + 110°C (-4°F + 230°F)
PFM (V)	-20°C + 180°C (-4°F + 356°F)
EPDM (Ethylene Propylene)	-40°C + 150°C (-40°F + 302°F)

Working Pressure - Betriebsdruck

25 Bar (360 PSI)

Connection / Disconnection Max. Pressure - Ein- und Auskoppelbar bis Max. Druck

15 Bar (220 PSI)

Flow size - Nennweite

451.08 8mm (3/8")

Standard version - Standardversion

Seals - Dichtung : Nitrile (N)

Material of standard version with plastic release ring

Material für die Standardversion mit Kunststoffauslösung

Socket Body -	Steel tenifer threaded
Kupplungsgrundkörper	Stahl teneferiert
Back Part -	Steel zinc nickel plated
Hinterteil	Stahl Zink-Nickel beschichtet
Sleeve -	Orange colour plastic
Hülse	Kunststoff, Farbe orange
Springs - Federn	Stainless steel - Edelstahl
Seals - Dichtungen	Nitrile (N)
Plug	Steel tenifer threaded
Nippel	Stahl teneferiert

Advantages


- The system perfectly fits to the ISO 4414, EN 983 safety requirements.
- Plug profile perfectly fits to the ISO 6150-C-14, AFNOR C-14 NF E 49-053
- 2 stage disconnection safety feature
- Through flow, minimum pressure loss
- Negligible Connecting Force
- Smart and Ergonomic features
- Ease of Handling
- Optimised Size

Vorteil

- Sicherheit gemäß ISO 4414, EN 983
- Stecknippel gemäß ISO 6150-C-14, AFNOR C-14 NF E 49-053
- 2 stufen Sicherheitsentriegelung
- Voller Durchgang, sehr geringer Druckverlust
- Einflache Bedienung, sehr geringe Kuppelkraft
- Kompakte Bauform



Flow Rate vs Pressure Drop Graph



451.08

451.08

Plastic sleeve socket with male thread / Kupplung mit Kunststoffdrehhülse und Aussengewinde



Socket / Kupplung	Size / Größe	Alternative Order No Alternative Bestellnr.	Order No / Bestellnr.	$\varnothing d$	$\varnothing d1$	L	L1	HEX.
	8	R203 00 299	H102.2450	BSP 3/8	32	73	63	24
	8	R203 00 300	H102.2451	BSP 1/2	32	75	63	24
	8	-	H102.2452	NPT 3/8	32	75	63	24
	8	-	H102.2453	NPT 1/2	32	80	63	24

451.08

Plastic sleeve socket with female thread / Kupplung mit Kunststoffdrehhülse und Innengewinde



Socket / Kupplung	Size / Größe	Alternative Order No Alternative Bestellnr.	Order No / Bestellnr.	$\varnothing d$	$\varnothing d1$	L	L1	HEX.
	8	R203 00 295	H102.2454	BSP 1/4	32	73	-	24
	8	R203 00 296	H102.2455	BSP 3/8	32	73	-	24
	8	R203 00 297	H102.2456	BSP 1/2	32	76	-	24
	8	-	H102.2457	NPT 3/8	32	74	-	24
	8	-	H102.2458	NPT 1/2	32	81	-	24

451.08

Plastic sleeve standard hose socket / Kupplung mit Kunststoffdrehhülse und Schlauchanschluss



Socket / Kupplung	Size / Größe	Alternative Order No Alternative Bestellnr.	Order No / Bestellnr.	$\varnothing d$	$\varnothing d1$	L	L1	HEX.
	8	R203 00 302	H102.2459	$\varnothing 8 - 5/16$	32	84	-	-
	8	R203 00 303	H102.2460	$\varnothing 10 - 3/8$	32	87	-	-
	8	R203 00 304	H102.2461	$\varnothing 13 - 1/2$	32	87	-	-

451.08

Male thread plug / Nippel mit Aussengewinde



Plug / Nippel	Size / Größe	Alternative Order No Alternative Bestellnr.	Order No / Bestellnr.	$\varnothing d$	$\varnothing d1$	L	L1	HEX.
	8	R255 00 101	H102.3029	BSP 1/4	-	55	44	17
	8	R255 00 102	H102.3030	BSP 3/8	-	57	44.5	19
	8	-	H102.3031	BSP 1/2	-	60	48	24
	8	R255 00 090	H102.3032	NPT 1/4	-	57	44.5	17
	8	R255 00 089	H102.3033	NPT 3/8	-	57	44.5	19
	8	R355 00 090	H102.3785	BSP 1/4	-	55	44	17
	8	R355 00 091	H102.3787	BSP 3/8	-	57	44.5	19
	8	-	H102.3789	BSP 1/2	-	60	48	24
	8	R355 00 092	H102.3801	NPT 1/4	-	57	44.5	17
	8	R355 00 093	H102.3803	NPT 3/8	-	57	44.5	19

*SS: Stainless Steel / Edelstahl